

St Albans

FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0331 630 4695

W: www.thebrickspecialists.com



PRODUCT TECHNICAL INFORMATION		TECHNICAL PROPERTIES TO BS EN 771-1	
BRICK CODE	MBS01600	TYPE	Handmade
CONFIGURATION	Handform	GROSS DRY DENSITY (KG/M ³ /TOLERANCE)	1720kg/m ³ (D1)
COLOUR	Red with white and dark shades	ACTIVE SOLUBLE SALTS	S2
APPEARANCE	Creased	COMPRESSIVE STRENGTH	≥20N/mm ²
SIZE Metric	215mm x 102.5mm x 65mm	THERMAL CONDUCTIVITY*	< -0.41 W/m.k
PACK SIZE	544	SIZE TOLERANCE (MEAN/RANGE)	T1/R1
INDIVIDUAL DRY BRICK WEIGHT	2.2kg	DURABILITY DESIGNATION	F2
		WATER ABSORPTION	<=15% _m /md
		INITIAL RATE OF WATER ABSORPTION (KG/(M ² . MIN))	1.5 - 4.0kg/m ² .min (IW3)
		REACTION TO FIRE	A1



The Brick Specialists

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

